

NASA TECHNICAL
MEMORANDUM



N71-19932

NASA TM X-2065

NASA TM X-2065

THIN FILM PENETRATION
BY HYPERVELOCITY MICROPARTICLES

by Anthony R. Lewis and Robert A. Walter

Electronics Research Center

Cambridge, Mass. 02139

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION • WASHINGTON, D. C. • MARCH 1971

1. Report No. NASA TM X-2065		2. Government Accession No.		3. Recipient's Catalog No.	
4. Title and Subtitle Thin Film Penetration by Hypervelocity Microparticles				5. Report Date March 1971	
				6. Performing Organization Code	
7. Author(s) Anthony R. Lewis and Robert A. Walter				8. Performing Organization Report No. C-137	
9. Performing Organization Name and Address Electronics Research Center Cambridge, Mass.				10. Work Unit No. 125-24-03-12-25	
				11. Contract or Grant No.	
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration				13. Type of Report and Period Covered Technical Memorandum	
				14. Sponsoring Agency Code	
15. Supplementary Notes					
16. Abstract <p>Carbonyl iron microparticles were accelerated electrostatically to velocities up to 25 km/s. Particles with selected velocities were impacted on thin parylene films mounted on 100-mesh electron microscope grids. The ratio of average hole-diameter to average particle-diameter increases from 1 to 7 as the velocity increases from 2 to 20 km/s. Particles whose diameters are greater than the film thickness punch a hole through the film whereas particles whose diameters are less than the film thickness break up during the impact interaction and thus enlarge the hole diameter beyond the particle diameter.</p>					
17. Key Words Film Penetration Hypervelocity Microparticles				18. Distribution Statement Unclassified - Unlimited	
19. Security Classif. (of this report) Unclassified		20. Security Classif. (of this page) Unclassified		21. No. of Pages 7	
				22. Price* \$3.00	

THIN FILM PENETRATION BY HYPERVELOCITY MICROPARTICLES

By Anthony R. Lewis and Robert A. Walter
Electronics Research Center

SUMMARY

Carbonyl iron microparticles were accelerated electrostatically to velocities up to 25 km/s. Particles with selected velocities were impacted on thin parylene films mounted on 100-mesh electron microscope grids. The ratio of average hole-diameter to average particle-diameter increases from 1 to 7 as the velocity increases from 2 to 20 km/s. Particles whose diameters are greater than the film thickness punch a hole through the film whereas particles whose diameters are less than the film thickness break up during the impact interaction and thus enlarge the hole diameter beyond the particle diameter.

INTRODUCTION

A number of micrometeoroid detectors depend upon the interaction of the impacting micrometeoroid with a thin film. For example, Goddard Space Flight Center has developed a thin film telescope* detector which has been successfully flown on a number of probes and satellites (ref. 1). This unit determines particle velocity by time-of-flight measurements between two thin-film arrays (Figure 1). The ionization produced by a particle penetrating the thin films is measured and also serves to initiate the "start" and "stop" pulses for the time-of-flight determination. The amount of ionization is indicative of the particle energy and composition but the quantitative relationship is, as yet, not fully known.

To gain a better quantitative understanding of the interaction we have impacted thin films (0.2 μm thick) of parylene with carbonyl iron spherules of known masses and velocities.

*The telescope detector consists essentially of a velocity measuring component and a momentum (or energy) sensitive component. These are usually mounted in a tube such that the direction of the impacting micrometeoroid can be determined and that the micrometeoroid penetrates the velocity-measuring component prior to impact on the momentum (or energy) sensor. Time-coincident output pulses are generally required from both sensors for an event to be considered a true impact as opposed to accidental or noise output pulses. The term 'telescope detector' is used in analogy to two-component nuclear particle detectors which perform similar measuring functions for nuclear particles.




Figure 1.- Micrometeroid detector developed by Goddard Space Flight Center

Although these initial data do not yield definitive results, they are interesting nonetheless in that they demonstrate some quantitative relationships and indicate the directions in which future work should proceed.

EXPERIMENT

Carbonyl iron spherules (Figure 2), with velocities up to 25 km/s, were impacted on thin plastic films. Acceleration to hypervelocities was accomplished electrostatically, using a 150-kv ion accelerator converted to microparticle acceleration (ref. 2). The performance of the accelerator is shown in Figure 3 where particle velocity is plotted as a function of particle size. Particle masses and velocities were selected and measured using the system described in reference 2.

Discs of parylene (TM - Union Carbide), 3 mm diameter, were punched from a 3-inch diameter, 0.2 μ m thick sheet of material. The discs were glued to a 100-mesh electron microscope grid, which was placed in a standard Hitachi electron microscope grid holder. The film was then examined with a transmission electron microscope for holes, cracks, and excessive glue. Grids with acceptable films were removed from the electron microscope still attached to the holder and mounted in the accelerator target chamber. This procedure assured that the parylene films were never touched after being inspected in the electron microscope. Double thin films of parylene were made by gluing discs to both sides of the electron microscope grid.

The films were impacted by microparticles in a selected velocity range. During bombardment, the velocities and masses of the impacting particles were measured. After bombardment, the film and holder were removed from the target chamber and re-examined, using the transmission electron microscope. The number of holes in the film and their sizes were recorded.





Figure 2.- Electron photo-
micrograph of carbonyl
iron powder


Figure 3.- Microparticle
velocity as a function
of particle size



RESULTS

Figure 4 shows a typical impact area on a single film viewed with the electron microscope. The holes were ($\sim 1 \mu\text{m}$ diameter) are caused by large, slow particles. The experimental results are summarized graphically in Figure 5 where the ratio of average hole-diameter to average particle-diameter is plotted against the velocity of the impacting particles. Each data point represents punctures by a number of particles whose velocity range is given by the horizontal bar. Uncertainties in the value of the ratio are given by the vertical bar. The number of particles used is given for each point. The value of the ratio increases from 1 to 6 as the impacting particle velocity increases from 2 to 10 km/s; above 10 km/s the ratio increases more slowly. One should note that this velocity dependence of the hole size to particle size ratio is similar to the velocity dependence found by Auer, et al. (ref. 3) for the ratio of crater size to the particle size when hypervelocity microparticles are impacted on a semi-infinite target. Auer's relationship is also represented in Figure 5. Since his microcrater data extends only up to 10 km/s it is not possible to compare it with our higher velocity puncture data which exhibit a decreasing slope of the curve. It would be interesting to extend the microcrater data to investigate if a similar "flattening out" characteristic can be observed.

Figure 4.- Typical impact area on a single thin film showing penetration






Figure 5.- Hole size - particle size ratio as a function of particle size

Another presentation of the puncture data is given in Figure 6 where the ratio of average hole-diameter to average particle-diameter is plotted against the average particle-diameter. The number of particles and the minimum, median, and maximum velocities of these particles are shown for each data point. Bars are not used to avoid cluttering the presentation.

At lower velocities the particle diameters exceed the film thickness, whereas at the high velocities the particle diameters are less than the film thickness. Figure 7 shows punctures of a double film, mounted at a slight angle to the beam, made by one large ($0.5 \mu\text{m}$ diameter) and several small ($0.25 \mu\text{m}$ and $\sim 0.1 \mu\text{m}$ diameter) hypervelocity particles. The large projectile (upper right-hand corner) passed cleanly through both films giving up little kinetic energy on doing so; an indication of this is the similarity in size of the two holes. The smaller particles broke up in the first film expending all their kinetic energy doing so. Debris of this break up can be seen on the second film. This mechanism explains qualitatively why the hole-diameter/particle-diameter ratio increases so rapidly when the particle size approaches the film thickness. This disintegration has also been reported by Auer, et al. (ref. 3) using $0.8 \mu\text{m}$ Fe projectiles on $0.8 \mu\text{m}$ Al foil.




Figure 6.- Hole size - particle size ratio as a function of particle size





Figure 7.- Double thin film showing penetration by large and small particles



REFERENCES

1. Nilsson, C.S.; and Wilson, D: The Micrometeoroid Experiment on the OGO-2 Satellite. NASA CR-100683, 1969.
2. Lewis, A.R.; and Walter, R.A.: Electrostatic Acceleration System for Hypervelocity Microparticles with Selected Kinematic Properties. NASA TN D-5780, 1970.
3. Auer, S.; Grun, E; Rauer, P.; Rudolph, V.; and Sitte, K.: Studies in Simulated Micrometeoroid Impact. Space Research VIII. North-Holland Publishing Co., Amsterdam, 1968, pp. 606-616.

FIRST CLASS MAIL



POSTAGE AND FEES PAID
NATIONAL AERONAUTICS AND
SPACE ADMINISTRATION

POSTMASTER: If Undeliverable (Section 158
Postal Manual) Do Not Return

"The aeronautical and space activities of the United States shall be conducted so as to contribute . . . to the expansion of human knowledge of phenomena in the atmosphere and space. The Administration shall provide for the widest practicable and appropriate dissemination of information concerning its activities and the results thereof."

— NATIONAL AERONAUTICS AND SPACE ACT OF 1958

NASA SCIENTIFIC AND TECHNICAL PUBLICATIONS

TECHNICAL REPORTS: Scientific and technical information considered important, complete, and a lasting contribution to existing knowledge.

TECHNICAL NOTES: Information less broad in scope but nevertheless of importance as a contribution to existing knowledge.

TECHNICAL MEMORANDUMS: Information receiving limited distribution because of preliminary data, security classification, or other reasons.

CONTRACTOR REPORTS: Scientific and technical information generated under a NASA contract or grant and considered an important contribution to existing knowledge.

TECHNICAL TRANSLATIONS: Information published in a foreign language considered to merit NASA distribution in English.

SPECIAL PUBLICATIONS: Information derived from or of value to NASA activities. Publications include conference proceedings, monographs, data compilations, handbooks, sourcebooks, and special bibliographies.

TECHNOLOGY UTILIZATION PUBLICATIONS: Information on technology used by NASA that may be of particular interest in commercial and other non-aerospace applications. Publications include Tech Briefs, Technology Utilization Reports and Technology Surveys.

Details on the availability of these publications may be obtained from:

SCIENTIFIC AND TECHNICAL INFORMATION OFFICE

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

Washington, D.C. 20546